

SUBGRADE	GRAMMAGE	MOISTURE	SCT CD	SCT INDEX
FL	g/m ²	%	kN/m	kN.m/kg
FL 110	110	8	1,93	17,2
FL 120	120	8	2,20	18,3
FL 135	135	8	2,48	18,3
FL 140	140	8	2,57	18,3
FL 150	150	8	2,75	18,3
FL 160	160	8	2,93	18,3
FL 175	175	8	3,20	18,3
FL 200	200	8	3,67	18,3

PROPERTY	GRAMMAGE	MOISTURE	SCT CD	SCT INDEX
TOLERANCES	± 5 %	± 1,5	- 10 %	- 10 %
TEST STANDARD	ISO 536	ISO 287	ISO 9895	ISO 9895

*Sampling is done according to EN ISO 186 Method. Conditioning: T= 23 ±1 °C and RH= 50 ± 3% in accordance with EN ISO 187.

**Unless otherwise stated, our product specifications are for the Top Side.

***Width Tolerance (-) 1 (+) 3 mm

****Reel Core ID: 100 (+/-) 2mm