

## WHITE TOP TESTLINER (WTTL)

KK-TS-016 Rev.03  
Date: 28.11.2024

SUBGRADE	GRAMMAGE	MOISTURE	SCT CD	SCT INDEX	BURST STRENGHT	BURST INDEX	BRIGHTNESS	COBB60 TOP
WTTL	g/m <sup>2</sup>	%	kN/m	kN.m/kg	kPa	kPa.m <sup>2</sup> /g	%	g/m <sup>2</sup>
WTTL 110	110	7	1,87	17	236	2,15	70	40
WTTL 120	120	7	2,04	17	258	2,15	70	40
WTTL 135	135	7	2,30	17	290	2,15	70	40
WTTL 160	160	7	2,72	17	328	2,05	70	40
WTTL 175	175	7	2,97	17	358	2,05	70	40

PROPERTY	GRAMMAGE	MOISTURE	SCT CD	BURST STRENGHT	BRIGHTNESS	COBB60 TOP
TOLERANCES	± 4%	± 1,5	-10%	-10%	-2	±10
TEST STANDARD	ISO 536	ISO 287	ISO 9895	ISO 2758	ISO 2470-1	ISO 535

\*Sampling is done according to EN ISO 186 Method. Conditioning: T= 23 ±1 °C and RH= 50 ± 3% in accordance with EN ISO 187.

\*\*Our products meet the EN 13430 Recyclability and EN 13432 Biodegradability Standard requirements.

\*\*\*Unless otherwise stated, our product specifications are for the Top Side.

\*\*\*\*Applied to 95 % of all determined measured single values. Single value is a calculated average of 5 samples measurements per sheet.

\*\*\*\*\*Width Tolerance (-) 1 (+) 3 mm

\*\*\*\*\*Reel Core ID: 100 (+/-) 2mm

[www.batikipas.com.tr](http://www.batikipas.com.tr)

"Paper&Board Manufacturers"