

COATED WHITE TOP TESTLINER (cWTTL)

KK-TS-024 Rev.03
Date: 04.09.2024

GRAMMAGE	THICKNESS	BULK	BURST STRENGTH	SCT CD	PPS	BRIGHTNESS TOP	COBB60' BACK	COBB60' TOP	SCOTT BOND
g/m ²	µm	cm ³ /g	kPa	kN/m	µm	%	g/m ²	g/m ²	J/m ²
160	176	1,1	340	3,60	2,6	82	100	50	200
180	198	1,1	380	3,70	2,6	82	100	50	200
200	220	1,1	420	4,00	2,6	82	100	50	200
210	230	1,1	440	4,10	2,6	82	100	50	200
230	252	1,1	470	4,30	2,6	82	100	50	200

PROPERTY	GRAMMAGE	THICKNESS	BURST STRENGTH	SCT CD	PPS	BRIGHTNESS TOP	COBB60' BACK	COBB60' TOP	SCOTT BOND	WIDTH TOLERANCE
TOLERANCES	(+/-) 3%	(+/-) 5%	(-) 15%	(-) 10%	(+) 0,5	(-) 2	(+/-) 50	(+/-) 20	(-) 30	(+) 3 mm
TEST STANDARD	ISO 536	ISO 534	ISO 2758	ISO 9895	ISO 8791-4	ISO 2470-2	ISO 535	ISO 535	ISO 15754	

*Sampling is done according to ISO 186 Method. Conditioning: T= 23 ±1 °C and RH= 50 ± 3%

**Our products meet the EN 13430 Recyclability and EN 13432 Biodegradability Standard requirements.

***Unless otherwise stated, our product specifications are for the Top Side.

****Reel Core ID: 100 (+/-) 2mm

www.batikipas.com.tr

"Paper&Board Manufacturers"